



**Product Name:**

**LIGHTHOUSE WHITE MAGIC SILICONIZED ACRYLIC SEALANT**

**PRODUCT DESCRIPTION:**

LIGHTHOUSE WHITE MAGIC Siliconized Acrylic Sealant is a very durable, all-purpose acrylic elastomeric adhesive sealant, with superlative adhesion to most construction surfaces and superior flexibility. It is available in white, black, almond, redwood, brown, bronze, cedar tan, pecan, and gray.

**PROMINENT FEATURES:**

- This product is vacuumized to remove all microscopic air and to ensure the maximum in durability and gunnability.
- Strong adhesive characteristics
- 45 year life expectancy
- Paintable
- Elastomeric
- Cured sealant is mildew resistant
- Soap and water clean-up
- Meets ASTM C-834, Type P, Grade -18°C
- Enhanced toolability for all climates

**Uses:** LIGHTHOUSE WHITE MAGIC Siliconized Acrylic Sealant provides water and weather protection by forming an airtight seal when used on interior and exterior surfaces such as wood, metal, concrete, brick, plaster, masonry, drywall, glass and ceramic tile. It is ideal for sealing seams, cracks and joints around doors, windows, woodwork, siding, flashing, air conditioners and kitchen and bathroom counters. It may be used on interior or exterior applications.

**Limitations**

- Do not use for structural repairs.
- Do not use below grade or under water.
- Not recommended for food surfaces.
- Application should be made when temperature of air and surface is 50°F. (10°C.) or above for a 24 hour period.
- If rain or threatening weather is expected within 8 hours, delay application until dry conditions exist.
- Allow new concrete to cure for 30 days before applying. After 30 days, test for alkali presence.
- Do not apply if pH is above 10.
- Do not apply if relative humidity is above 90%.
- Do not freeze.

**Surface Preparation**

All surfaces must be firm and free of dirt, oil, grease, efflorescence, mildew and loose material. Unsound masonry must be wire brushed or blasted for a firm surface. Dirt, loose contaminates and chalk are best removed by high pressure chemical and water blasting. Any chalk or porous coating not removed by pressure washing must first be sealed with an alkali resistant surface conditioner, such as VIP1200 Surface Conditioner. Prior to applying VIP1200, allow stucco and concrete block mortar to cure 3 days. Poured in-place precast concrete should be allowed to cure 7 days. To remove mildew, scrub with a solution of 3 heaping teaspoonful of Trisodium Phosphate (TSP), 1 quart of Hypochlorite Household bleach and 3 quarts of warm water (wear protective goggles and impervious gloves. Follow manufacturer's directions when working with cleaning solutions). Rinse thoroughly and allow to dry. Non-structural shrinkage cracks (larger than 1/16" ) and non-structural movement cracks larger than 1/16" up to 1/4") must be treated and repaired accordingly.

**Method of Application**

1. Cut nozzle at a 45° angle to desired thickness to bead. Apply with a standard caulking gun.  
Use a steady pressure to completely fill joints.
2. For a neat appearance, smooth bead with a brush or cloth.
3. For best results, cured beads should be between 1/8"-1/2" wide and 1/8-1/4" deep.  
Important: Use Backer Rod for cracks and seams deeper than 1/4".
4. Remove excess material before cure with a moistened cloth. Clean up tools with water.
5. May be painted over with latex or oil based paints when dry (generally within 4 to 6 hours, depending on climatic conditions).
6. Do not apply when rain is expected. Not intended for underwater use.

**Coverage:** A 1/8"x1/4" bead will yield approximately 50 linear feet of sealant per cartridge.

## TECHNICAL INFORMATION

Property	Value (1)	Test Method
% Solids by Weight	82.0 +/- 2%	Lab Value
Density	13.4 lb/gal	Calculated
Extrudability (g/sec)	16.85 g/sec	C 1183 Procedure B
Hardness A	50.2	C661
Tack-free Time	45 min	D 2377
Freeze/Thaw Stability	Passes 5 cycles	Lab Value
Artificial Weathering	Pass	C 732
Volume Shrinkage	17.3%	C 1241
Low Temp Flexibility 0 &-18C	Pass	C 734
Recovery	95.2%	C 736
Adhesion Loss	0.0%	C 736
Slump	0	D 2202
Stain Index	Pass	D 2203
Flame Spread Index	5	ASTM E84-13a
Smoke Developed Index	0	ASTM E84-13a
VOC (less water and exempt compounds):	<34 g/L	Calculated
VOC (Carb Non Chem Curing N.A.)	<1.5%	Calculated

(1) Average value. Actual value may vary.

Typical product data values should not be used as specifications. Assistance is available by contacting Momentive Performance Materials at (866)-275-4372.

Packaging: 10.1 fluid oz. plastic cartridge. Packed 12 per carton.

### Clean Up

Clean all equipment immediately after use with warm, soapy water.

### Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information by the manufacturer of such other materials.

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Limited Warranty

Manufacturer warrants this product meets Manufacturer's specifications if properly stored and applied. If not satisfied, return proof of purchase for refund. Manufacturer shall not be liable for damages in excess of the purchase price. This is the sole and exclusive remedy/liability for product defects/failure. **THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS.**

Momentive and M-design logo are trademarks of Momentive Performance Materials Inc.  
Copyright 2014 Momentive Performance Materials Inc., all rights reserved.